

ME-1505 – Södra Forest Estonia, aspen pulpwood

Measurement place:	All measurement places
Seller:	All sellers
Buyer:	Södra Forest Estonia OÜ
Measurement method:	Stack measurement with estimation of solid volume percentage
Assortment/species:	Pulpwood; aspen
Measurement instructions:	Swedish Instructions

The difference with Swedish Instructions:

Forest rot:	Dark rot, soft rot and rot holes. Maximum accepted forest rot in individual log: 36% of the end surface of the log (under bark) (or 60% of the end diameter (under bark)) may be damaged by rot. Logs where rot exceeds the limit are rejected.
-------------	--

No volume deduction due to forest rot is made!